



Development of an 8x8 CPW Microwave Kinetic Inductance Detectors (MKIDs) Array

Main author:

LI Jing

Co-authors:

Furukawa N., RIKEN Center for Advanced Photonics, Japan

LI Jing, Purple Mountain Observatory, China

LIN Zhen-Hui, Purple Mountain Observatory, China

LIU Dong, Purple Mountain Observatory, China

Mima S., RIKEN Center for Advanced Photonics, Japan

Otani C., RIKEN Center for Advanced Photonics, Japan

SHI Sheng-Cai, Purple Mountain Observatory, China

Introduction

China is planning to construct an observatory at Dome A, Antarctica, which has been found to be the best site (with low perceptible water vapor and low atmospheric boundary layer) on the earth for THz and Optical/IR astronomy. One of the telescopes to be built there is a 5-m THz telescope (DATE5) targeting at 350 μ m and 200 μ m atmospheric windows. One science case for the DATE5 is to observe extreme starburst galaxies at different redshifts to better understand the nature and evolution of these enigmatic and important objects. Therefore, we are going to develop an imaging camera with 1024-pixel. We are currently developing a detector array demonstrator to meet such a requirement in the future.

The detector array demonstrator has 8x8 pixels and will work at 0.35 THz, which is chosen to demonstrate the performance of the detector array on a small sub-millimeter telescope (POST, with a diameter of 30cm) situated at Delingha, China. As is well known, microwave kinetic inductance detectors (MKIDs) use frequency domain multiplexing that allows thousands of pixels to be read out over a single microwave transmission line followed by a cryogenically cooled low noise amplifier. Furthermore, a large number of MKIDs can be integrated like a filter bank to realize on-chip spectrometers such as DESHIMA and SuperSpec. Hence we choose MKIDs to develop our detector array demonstrator. The MKIDs make use of TiN superconducting films with a critical temperature of approximately 4.5 K, which can be operated at temperatures of \sim 0.3K. Furthermore, TiN MKIDs can reach a noise equivalent power (NEP) below 1×10^{-19} W/Hz $^{0.5}$, which is a sufficiently high sensitivity for ground-based astronomical

observations. The 8x8 TiN MKIDs will be integrated with a micro-lens array of 8x8 0.95-mm hyper-spherical Si lens with a separation of 2 mm between individual lens. The readout for this MKIDs detector array demonstrator is similar to others, but adopting a commercial arbitrary wave-function generator to generate 64-tone input signal. The 0.3K refrigerator for the demonstrator is a He3 two-stage sorption cooler (CRHe7) based on a liquid helium cryostat, which offers over 10 hours continuous cooling with a total heat load of up to 20 μ W. In this paper, we mainly introduce the design, fabrication, and characterization of the 8x8 TiN MKIDs.

MKIDs: DESIGN AND FABRICATION

We adopted the coplanar-waveguide (CPW) type resonator to design our 8x8 TiN MKIDs array because it has a relatively simple architecture of only one thin-film layer on the substrate. This kind of resonator has a quarter-wavelength transmission line with one end capacitively coupled to a feed line and the other matched to a planar antenna (twin-slot antenna, for example).

We started from the design of the coupler, which is an elbow structure at the end of the resonator near the feed line. With this layout, we can make the feed line and the coupler share the same metal section as the ground. The CPW line for the coupler was designed to have a 3 μ m center stripe and 2 μ m gaps. The ground space between the feed line and the coupler was set as 2 μ m. Based on the structure, we can get different coupling strength by changing only the length of the coupler. Using an electromagnetic microwave simulator, we studied the dependences of the coupling strength upon the coupling quality factor (Q_c), the resonance frequency (f_0) and the coupler length (L_c).

The 8x8 MKIDs array was fabricated in the cleanroom of RIKEN Center for Advanced Photonics (Japan). As introduced before, we chose TiN superconducting films for this MKIDs detector array. MKIDs based on TiN superconducting films have a few advantages including a) T_c can be controlled between \sim 0-5 K by the components of Ti and N₂; b) quasi-particle lifetime is around 10-200 μ s; c) low loss in the superconducting state. Firstly, a 100-nm thick TiN film was deposited on a high resistivity Si wafer in a DC magnetron sputtering system. Secondly, the CPW lines were defined in contact lithography by a mask aligner. Thirdly, the etching course was done in an ICP machine.

MEASURED PERFORMANCE

For the fabricated 8x8 TiN MKIDs array, we mainly measured its Q factors and the dependence of Q factors upon the bath temperature and the input power for the multiplexing readout. The measurements were done simply by a scalar network analyzer to the 8x8 TiN MKIDs array and a following 0.1~12 GHz cryogenically cooled low-noise amplifier, which has an equivalent noise temperature of 5 K and gain of approximately 35 dB.

Conclusions

We have designed and fabricated an 8x8 TiN MKIDs array. Its transmission characteristic has been measured with respect to the bath temperature and input power. The temperature dependence follows that predicted by the Mattis-Bardeen theory, while the resonance frequency and the quality factor are both insensitive to the input power when it is below -40dBm.